



TERMS AND CONDITIONS FOR ULTRATECH LITECON

- UltraTech Litecon shall have a strength of 2-3 MPa at 28 days with a density of less than 1000 Kg/m³.
- This material cannot be used as a wearing coat and would require screed, tiles, pavers or any protection layer.
- This is a non-structural concrete and hence is not designed to take dead/live loads beyond its designed strength.
- Curing should be done as per IS 456-2000, to avoid shrinkage cracks. Concrete surface should not be allowed to dry. Water sprinkling or early curing should be commenced at site or concrete surface shall be protected by covering plastic sheet immediately after placing the concrete.
- The concrete surface shall be protected with a protection layer immediately after the water curing process.